

**Quality :** Sonora-185AS  
**Fabric Weight :** 185gs (±5%)m  
**Composition :** 80% Cotton, 19% Polyester, 1% Antistatic  
**Usable Width :** 150cm  
**Nominal Length :** 100cm  
**Weave :** Plain 1/1  
**Application :** Light workwear shirts, trousers and coveralls



**Washing Instructions :**


Do not bleach, do not boil, do not use soap based products only detergents

### Physical Properties

	Warp	Weft
Tensile Strength: (BS EN ISO 13934-1:1999)	750 N	430 N
Tear Strength: (BS EN ISO 13937-2:2000)	19 N	18 N
Washing Shrinkage: (ISO 5077 after 5 washes ISO 15797)	3%	3%
Abrasion Resistance: (12kPa) (BS EN ISO 12947-2:1999)	17,000 rubs	
Pilling Resistance: (BS EN ISO 12945-2:2001)	4	

### Other Properties

<b>Flame retardant</b>	EN ISO 11612 A1, B1,C1
<b>Anti static</b>	EN 1149-5 (1149-3 method 2)

### Colour Fastness

	Light	Mid	Dark	Special colors
	Orange, Yellow	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
<b>Wash Fastness BS EN ISO 105-C06: Method E2S (95°C)</b>				
Colour Change	4--5	4--5	4--5	4--5
Stain on Polyester	4	4--5	4	4
Stain on Cotton	4--5	4--5	4--5	4
<b>Rub Fastness BS EN ISO 105-X12:1995</b>				
Wet	4	3	3	3
Dry	4--5	4	4	4
<b>Light Fastness BS EN 20105/ISO 105-B02</b>				
Light Fastness	3	4	4	4

The data quoted is based upon specific materials and tested by sources believed to be reliable and XM Textiles make no guarantee, express or implied as to use, handling or possession of its products.

Authorised by: XM Quality control department

Date: May 14, 2016

These values are for guidance only, some colours will be better others worse.

Please contact your XM Textiles representative for specific shade details.

XM Textiles (Head Office)  
 Office 2402-2403, 24-th Floor,  
 Zhongyi International Commercial Plaza,  
 1833 Zhongshan North Road, Shanghai, China  
 Zip 200061  
 Telephone: +86 (21) 5240-1156  
 www.xmfireline.com

XM Textiles Europe  
 Dariaus ir Gireno st. 42A  
 Office 510  
 Vilnius LT – 02189  
 Lithuania  
 Telephone: +370 (347) 20299  
 www.xmfireline.com

XM Textiles Spain  
 Parque Empresarial Prado del Espino  
 C/Impresores, 20, oficina A-12  
 28660 Boadilla del Monte, Madrid  
 Spain  
 Telephone: +34 91 060 28 84  
 www.xmfireline.com